IN THE CLAIMS:

The following listing of claims will replace all prior versions, and listings, of claims in the application:

1 (Currently Amended) An organic-inorganic hybrid material having comprising a metal oxide matrix having one kind or plural kinds of metal atoms, and a ligand bonded to the metal atom by chelating.

wherein the metal atom is selected from typical metals or transition metals.

2 (Withdrawn) An organic-inorganic hybrid material according to claim 1, wherein the organic hybrid material has a peak of an absorption spectrum between 350 nm and 800 nm.

3 (Withdrawn) An organic-inorganic hybrid material according to claim 1, wherein the ligand shows a light-emitting property by chelating the metal atom.

4 (Withdrawn) An organic-inorganic hybrid material according to claim 1, wherein the organic hybrid material has a peak of an emission spectrum between 380 nm and 760 nm.

5 (Currently Amended) An organic-inorganic hybrid material according to claim 1, wherein the ligand shows semiconductivity by chelating the metal atom. wherein the organic-inorganic hybrid material shows semiconductivity.

6 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a phenolic hydroxy group in the ligand is bonded to the

metal atom,

wherein the ligand has a phenolic moiety, and an oxygen atom of the phenolic moiety is bonded to the metal atom, and

wherein the ligand further has a heterocycle with a nitrogen atom as a hetero atom[[,]] and chelates the metal atom by the oxygen atom and the nitrogen atom.

7 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a phenolic hydroxy group in the ligand is bonded to the

metal atom,

wherein the ligand has a phenolic moiety, and an oxygen atom of the phenolic moiety is bonded to the metal atom, and

wherein the ligand further has a carbonyl group[[,]] and chelates the metal atom by the oxygen atom of the phenolic moiety and the carbonyl group.

8 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherien an oxygen atom from a phenolic hydroxy group in the ligand is bonded to
the metal atom,

wherein the ligand has a phenolic moiety, and an oxygen atom of the phenolic moiety is bonded to the metal atom, and

wherein the ligand further has an azomethyne group[[,]] and chelates the metal atom by the oxygen atom of the phenolic moiety and the azomethyne group.

9 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a carboxyl group in the ligand is bonded to the metal atom,

wherein the ligand has a carboxyl moiety, and an oxygen atom of the carboxyl moiety is

bonded to the metal atom, and

wherein the ligand further has a heterocycle with a nitrogen atom as a hetero atom[[,]] and chelates the metal atom by the oxygen atom of the carboxyl moiety and the nitrogen atom.

10 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a carboxyl group in the ligand is bonded to the metal atom,

wherein the ligand has a carboxyl moiety, and an oxygen atom of the carboxyl moiety is

bonded to the metal atom, and

wherein the ligand further has a carbonyl group[[,]] and chelates the metal atom by the oxygen atom of the carboxyl moiety and the carbonyl group.

11 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a carboxyl group in the ligand is bonded to the metal atom,

wherein the ligand has a carboxyl moiety, and an oxygen atom of the carboxyl moiety is

bonded to the metal atom, and

wherein the ligand further has a azomethyne group[[,]] and chelates the metal atom by the oxygen atom of the carboxyl moiety and the azomethyne group.

12 (Currently Amended) An organic-inorganic hybrid material according to claim 1,

wherein an oxygen atom from a hydroxylamino group in the ligand is bonded to the

metal atom,

wherein the ligand has a hydroxylamino moiety, and an oxygen atom of the hydroxylamino moiety is bonded to the metal atom, and

wherein the ligand further has a carbonyl group, and chelates the metal atom by the oxygen atom of the hydroxylamino moiety and the carbonyl group.

13 (Currently Amended) An organic-inorganic hybrid material according to claim 1, wherein a ligand having any structure of 8—hydroxyquinoline and derivatives thereof, 10—hydroxybenzo—quinoline and derivatives thereof, 2—(2—hydroxyphenyl) benzoxazole and derivatives thereof, 2—(2—hydroxyphenyl) benzothiazole and derivatives thereof, 2—(2—hydroxyphenyl) pyridine and derivatives thereof, 3—hydroxyflavone—and derivatives thereof, 5—hydroxyflavone—and derivatives thereof, salicylideneamine and derivatives thereof, picolinic acid and derivatives thereof, coumarin—3—carboxylic acid and derivatives thereof, salicylideneamino acid and derivatives thereof, N—benzoyl—N—phenyl—hydroxylamine and derivatives thereof is used as the ligand.

wherein the ligand has a structure selected from 8-hydroxyquinoline moiety, 10-hydroxybenzoquinoline moiety, 2-(2-hydroxyphenyl)benzoxazole moiety, 2-(2-hydroxyphenyl)benzoimidazole moiety, 2 - (2-hydroxyphenyl)pyridine moiety, 3-hydroxyflavone moiety, 5-hydroxyflavone moiety,

salicylideneamine moiety, picolinic acid moiety, coumarin-3-carboxylic acid moiety, salicylidene aminoacid moiety, benzylideneamino acid moiety, N-benzoyl-N-phenylhydroxylamine moiety, N-cynnamoyl-N-phenylhydroxylamine moiety.

14 (Currently Amended) The organic-inorganic hybrid material according to any one of elaims claim 1 to 13,

wherein the metal atom is any of selected from the group consisting of magnesium, calcium, strontium, barium, scandium, yttrium, lanthanum, titanium, zirconium, hafnium, zirc, aluminum, gallium, and indium.

15 (Currently Amended) The organic-inorganic hybrid material according to any one of elaims claim 1 to 13, further including a silica moiety or an organosiloxane moiety wherein the metal is silicon.

16 (Currently Amended) The organic-inorganic hybrid material according to any one of elaims claim 1, to 13, further including comprising an aromatic moiety compound.

17 (Original) The organic-inorganic hybrid material according to claim 16, wherein the aromatic compound is an organic pigment, an organic light emitter, or an organic semiconductor.

18-19 (Canceled)

- 20 (Withdrawn) A light-emitting device using the carrier-injection type electroluminescent device described in claim 18.
- 21 (Withdrawn) A light-emitting device using the intrinsic electroluminescent device described in claim 19.
- 22 (Withdrawn) A glass product coated with the organic-inorganic hybrid material described in any one of claims 1 to 13.
- 23 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing a coloring property by chelating the metal atom, and an organic solvent.
- 24 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing a light-emitting property by chelating the metal atom, and an organic solvent.
- 25 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing semiconductivity by chelating the metal atom, and an organic solvent.

26 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a phenolic hydroxy group and a heterocycle with a nitrogen atom as a hetero atom, and an organic solvent.

27 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a phenolic hydroxy group and a carbonyl group, and an organic solvent.

28 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a phenolic hydroxy group and an azomethyne group, and an organic solvent.

29 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and a heterocycle with a nitrogen atom as a hetero atom, and an organic solvent.

30 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and a carbonyl group, and an organic solvent.

- 31 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and an azomethyne group, and an organic solvent.
- 32 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a hydroxylamino group and a carbonyl group, and an organic solvent.
- 33 (Withdrawn) A composition for coating application, including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound chelating the metal atom, and an organic solvent, wherein the organic compound is any of 8 hydroxyquinoline and derivatives thereof, 10 hydroxybenzo quinoline and derivatives thereof, 2 (2 hydroxyphenyl) benzothiazole and derivatives thereof, 2 (2 hydroxyphenyl) benzoimidazole and derivatives thereof, 2 (2 hydroxyphenyl) pyridine and derivatives thereof, 3 hydroxyflavone and derivatives thereof, 5 hydroxyflavone and derivatives thereof, salicylideneamine and derivatives thereof, picolinic acid and derivatives thereof, coumarin 3 carboxylic acid and derivatives thereof, salicylideneamino acid and derivatives thereof, N benzoyl N phenyl hydroxylamine and derivatives thereof.

34 (Withdrawn) The composition for coating application according to any one of claims 23 to 33, wherein the metal atom is any selected from the group consisting of magnesium, calcium, strontium, barium, titanium, zirconium, hafnium, zinc, aluminum, gallium, and indium.

35 (Withdrawn) The composition for coating application according to any one of claims 23 to 33, further including an alkoxysilane, an organoalkoxysilane, and/or an organosiloxane.

36 (Withdrawn) The composition for coating application according to claim 35, wherein the number of silicon atoms of the alkoxysilane, the organoalkoxysilane, and/or the organosiloxane is 0.5 equivalent or more and 10 equivalents or less for the number of the metal atoms.

37 (Withdrawn) The composition for coating application according to any one of claims 23 to 33, wherein the amount of the organic compound is 1 equivalent or less for the metal alkoxide and/or the metal salt.

38 (Withdrawn) The composition for coating application according to any one of claims
23 to 33, wherein the organic solvent is an organic solvent including a lower alcohol, tetrahydrofuran, or acetonitril.

- 39 (Withdrawn) The composition for coating application according to claim 38, wherein the lower alcohol any selected from the group consisting of methanol, ethanol, n-propanol, isopropanol, n-butanol, sec-butanol, and tert-butanol.
- 40. (Withdrawn) The composition for coating application according to any one of claims 23 to 33, further including water.
- 41 (Withdrawn) The composition for coating application according to claim 40, wherein the amount of the added water is 2 equivalents or more and 6 equivalents or less for the metal alkoxide and/or the metal salt.
- 42 (Withdrawn) The composition for coating application according to any one of claims 23 to 33, further including a chemical modifier.
- 43 (Withdrawn) The composition for coating application according to claim 42, wherein the chemical modifier is β -diketone.
- 44 (Withdrawn) The composition for coating application according to claim 42, wherein the amount of the added chemical modifier is 0.5 equivalent or more and 6 equivalents or less for the metal alkoxide and/or the metal salt.

45 (Withdrawn) The composition for coating application described in any one of claims 23 to 33, further including an aromatic compound.

46 (Withdrawn) The composition for coating application according to claim 45, wherein the aromatic compound is an organic pigment, an organic light emitter, or an organic smieoneductor.

47 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing a coloring property by chelating the metal atom, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

48 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing a light-emitting property by chelating the metal atom, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

49 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application

including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound showing semiconductivity by chelating the metal atom, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

50 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a phenolic hydroxy group and a heterocycle with a nitrogen atom as a hetero atom, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

51 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a phenolic hydroxy group and a carbonyl group, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

52 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal

salt, an organic compound having a phenolic hydroxy group and an azomethyne group, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

53 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and a heterocycle with a nitrogen atom as a hetero atom, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

54 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and a carbonyl group, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

55 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a carboxyl group and an azomethyne group, and an organic

solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

56 (Withdrawn) A method of manufacturing an organic-inorganic hybrid material, comprising a first step of performing wet coating of a composition for coating application including at least a metal alkoxide having one kind or plural kinds of metal atoms and/or a metal salt, an organic compound having a hydroxylamino group and a carbonyl group, and an organic solvent, on a base material, and a second step of calcining at a temperature of 100 °C or more and 300 °C or less under an atmospheric pressure or under a reduced pressure.

57 (Canceled)

58 (Withdrawn) The method of manufacturing the organic-inorganic hybrid material according to any one of claims 47 to 56 wherein the composition for coating application further includes β -diketon as a chemical modifier.

59 (Withdrawn) The method of manufacturing the organic-inorganic hybrid material according to any one of claims 47 to 56, wherein the wet coating is any of a dip coating method, a spin coating, and an inkjet method.

60. (Withdrawn) An organic-inorganic hybrid material according to claim 1, wherein the ligand shows a coloring property by chelating the metal atom.